

TEKNİK ÖZELLİKLER / Technical Specifications

110 gr/m² OFSET (Offset)

TEST METODU

TESTING METHOD

GRAMAJ (gr/m²)

BASIS WEIGHT (gr/m²)

110 ± 1,5

Tappi 410

KALINLIK (mic.)

CALIPER (mic.)

133 ± 3

Tappi 411

NEM (%)

MOISTURE (%)

4,5 ± 0,5

Tappi 412

MUKAVEMET (m)

BREAKING LENGHT (m)

MD

4.000 min

Tappi 404

MUKAVEMET (m)

BREAKING LENGHT (m)

CD

2.000 min

Tappi 404

BEYAZLIK (%)

BRIGHTNESS

100,0 min

Tappi 525

SARILIK

YELLOWNESS

-25,0 ± 2,0

Tappi 525

COBB (60 sn. gr/m²)

COBB (60 sec. gr/m²)

28 ± 4

Tappi 441

OPASİTE (%)

OPACITY (%)

94 min

Tappi 519