

TEKNİK ÖZELLİKLER / Technical Specifications

90 gr/m² IVORY OFFSET

TEST METODU

TESTING METHOD

GRAMAJ (gr/m²)

BASIS WEIGHT (gr/m²)

90 ± 1,5

Tappi 410

KALINLIK (mic.)

CALIPER (mic.)

110 ± 2

Tappi 411

NEM (%)

MOISTURE (%)

4,5 ± 0,5

Tappi 412

MUKAVEMET (m)

BREAKING LENGHT (m)

MD

4.000 min

Tappi 494

MUKAVEMET (m)

BREAKING LENGHT (m)

CD

2.000 min

Tappi 494

BEYAZLIK (%)

BRIGHTNESS

60 min

Tappi 525

SARILIK

YELLOWNESS

13 / 15

Tappi 525

COBB (60 sn. gr/m²)

COBB (60 sec. gr/m²)

24 ± 4

Tappi 441

CIE

CIE

35 min.

Tappi 525

OPASİTE (%)

OPACITY (%)

91 min.

Tappi 519