

SORA barrier OGR WS

KIT 5

Parameter	Standard						Tolerance
Grammage [g/m ²]	ISO 536	30	37	40	45	50	± 2
Smoot. Bendtsen [ml/min]	ISO 8791- 2	200	200	200	200	200	± 50
Tensile strength (MD) [kN/m]	DIN EN ISO 1924	3,0	3,5	4,0	4,5	5,0	
Tensile strength (CD) [kN/m]	DIN EN ISO 1924	1,7	2,0	2,2	2,5	2,8	
Wet strength [%]	DIN 53112	12	12	12	12	12	min
Burst [kPa]	ISO 2758	150	170	190	200	210	
Moisture content [%]	ISO 287	5,5	5,5	5,5	5,5	5,5	
Cobb ₆₀ [gH ₂ O/m ²]	ISO 535	20	20	20	20	20	± 5
KIT test		5	5	5	5	5	
ISO Brightness [%]	ISO2470-2 (D65/10°)	85	85	85	85	85	

Given values can be used as guide values only and can be changed without prior notice.

For a valid specification, please refer to the one most recently published on the website www.goricane.si.

Information on the supplies of FSC® and PEFC certified products are available in the Sales department.

