

SORA face

SORA face is a woodfree one—side coated label paper.



face

TS — 5.1. 2023

	STANDARD	70	80	90	100	110	Tolerance
GRAMMAGE [g/m ²]	ISO 536	70	80	90	100	110	± 2
SPEC. VOLUME [cm ³ /g]	ISO 534	0.88	0.88	0.88	0.93	0.93	± 0.05
THICKNESS [μm]	ISO 534	62	71	79	93	102	
SMOOT. BENDTSEN FACE SIDE [ml/min]	ISO 8791-2	25	25	25	30	30	± 25
REL. HUMIDITY [%]	DIN 53118	47.5	47.5	47.5	47.5	47.5	± 7.5
D65 BRIGHTNESS [%]	ISO 2470-2 (D65/10°)	95	95	95	95	95	± 2
CIE WHITENESS [%]	ISO 11475 (D65/10°)	120	120	120	120	120	
OPACITY [%]	ISO 2471	89	92	94	96	96	± 2

Given values can be used as guide values only and can be changed without prior notice.
For a valid specification, please refer to the one most recently published on the website www.goricane.si.
Information on the supplies of FSC® and PEFC certified products are available in the Sales department.



ISEGA

GORIČANE