

TECHNICAL DATA SHEET - SNOWBRIGHT

Parameter	Value	Tolerance	Comment
Brightness	75	-1/+0.5 g/m ²	As specified by Customer
Shade	Standard 9 (Creamy) or 4 (Bluish)	+/- 0.4	As specified by customer
Basis Weight	50 to 90 g/m ²	-2/+3 g/m ²	As specified by Customer
Bulk / Volume	1.8 / 18 to 2.4 / 24		As specified by Customer
Caliper	90 to 180 micron	+/- 4 micron	180 micron maximum
Opacity	83 to 96	+/- 1	Dependant on grammage/caliper
Moisture	9%	+/- 0.5	
Tear	200 to 450 mN		
Tensile	2.00 to 4.50 kN/m		
Main furnish	85 to 90% mechanical groundwood		
Secondary furnish	10 to 15% Cellulose		
Wrapping	Kraft wrappers		2 layers
Cores	76mm strawboard		152mm cores on request
Joins	Maximum 2 joins per reel		Marked by red line on reel
Reel Diameter	1000mm - 1150mm		As specified by customer
Accreditation	FSC	Volume Credit	FSC Paper on request
Printing proposals	48 lines/cm	Absolutely max. 54 lines/cm	Depends on reprographic job

All paper supplied according to the *General Trade Rules for Sales of Paper and Paperboard*

Should Technical Data be required for a specific grammage / caliper combination these can be provided upon request